

## Flame Retardant Fiberglass Tape

Adhesive Liner	Backing:	Fiberglass Clot	Fiberglass Cloth	
	Adhesive:	Bromide-Free	Bromide-Free Acrylic	
	Liner:	LDPE Film	LDPE Film	
	Colors:	White Printed	White Printed	
	Airbus ABI 757-SL-25- 777-SL-25- <b>Standard</b>	Specifications: Meets FAR 25.853(a) & 25.855(d), BMS5-146         Airbus ABD0031, Para 7.3.2& 7.4; Boeing 737-SL-25-115-B,         757-SL-25-085-B, 747-SL-25-195-B, 767-SL-25-112-B,         777-SL-25-037-B         Standard Sizes*:       1in, 2in, 3in and 4in x 36yd		
Applications				
<ul> <li>Cargo pit applications for freight carrying aircraft</li> <li>Challenging applications where high adhesion and flame resistance is critical</li> </ul>		<ul><li>liners</li><li>Covering pins</li></ul>	Covering pins & rivets Metal surface protection during soldering or	
Features			Benefits	
		<ul> <li>Resists flame p</li> <li>Lightweight cc</li> <li>Conformable t</li> <li>Meets EU Direc</li> <li>Repositionable</li> <li>Resists flagging</li> <li>Meets requirer</li> <li>compartments</li> </ul>	Resists flame penetration for added safety Lightweight construction - saves money Conformable to handle curves and corners Meets EU Directive 76/769/EEC Repositionable and clean removal Resists flagging and lifting Meets requirements for use in aircraft cargo compartments	
Physical Properties				
Adhesion to Steel45 ofTensile Strength134Weight6.8 ofOperating Temperature-40 toExiting Time0.6 ofBurn Length3Flame PenetrationN	mils pz/in lb/in pz/yd <sup>2</sup> p 275°F 6 sec 3" I/A	Metric UOM 177.8 mic 4.93 N/cm 234.67 N/cm 210 g/m <sup>2</sup> -40 to 135° C	Test Method ASTM D-1000 PSTC-101 ASTM D-1000 ASTM D-1000 FAR 25.853(a)/25.855(d) FAR 25.853(a) FAR 25.855(d) FAR 25.853(a)	
After Glow 0:	sec		FAR 25.855(d)	

\* Other sizes may be available. Contact your sales representative.

Recommended Storage Conditions: 40-60% Humidity, 60°F-80°F

Standard Shelf Life (at 25C): 24 months from date of manufacture.

The information presented herein was prepared at BERRY PLASTICS CORPORATION (25 Forge Parkway Franklin, MA 02038) by qualified technical personnel. To Berry Plastics' knowledge it is true and accurate. However, the information and recommendations are furnished for these products with the understanding that the purchaser or user, as the case may be, will independently determine that the product is suitable for the intended use, and that such use complies with all applicable federal, state and local laws and regulations. The data are submitted only for the user's information and consideration, and do not constitute a warranty of any kind (including but not limited to a warranty of merchantability or of fitness for a particular purpose), or a representation for which BERRY PLASTICS assumes any legal responsibility.



For Pricing and Information please contact distributor: **KIEPURA AVIATION CORP.** 61 Church St. Littleton, NH 03561 Tel: 603-444-3459 / Fax: 603-444-0790 Toll Free: 1-888-522-8273 (USA/Canada) Email: jane@kiepuraaviation.com www.kiepuraaviation.com