

## PRODUCT INFORMATION SHEET

Arlon Product Number T2020-R004

MOX 602

## PRODUCT DESCRIPTION

1.0 inch wide x 0.020" thick, red, triangular cross-section, silicone, self-fusing tape.

**Design / Construction** 

Interleave: 0.001" PET

**Product:** Cured self fusing silicone rubber

Cross-Section: Triangular

<u>Rubber Thickness</u> <u>Value</u> <u>Method</u>

Overall Thickness: 0.020" Arlon SQA-TMS-003

Product Color: Red, Black

## **PROPERTIES**

PROPERTIES			
Silicone Compound Properties		<u>Value</u>	<u>Method</u>
Tensile Strength	psi	1179	ASTM D 412
Elongation	%	732	ASTM D 412
Tear Strength	ppi	137	ASTM D624
Durometer	<b>Shore A Points</b>	49	ASTM D 2240
Specific Gravity		1.20	Arlon SQA-TMS-024
Product Properties		<u>Value</u>	<u>Method</u>
Dielectric Strength	volts/mil	649	ASTM D 149
Bond Strength	lb/in	2.5	Arlon SQA-TMS-015
Water absorption	%	0.2	Arlon SQA-TMS-016

## SHELF LIFE & CONTINUOUS OPERATING TEMPERATURE

**Product Shelf Life** 

12 months from DOM @ 70°F

Note: Shelf life is defined as the duration of time for which the product will meet the physical characteristics outlined on this page.

It does not guarantee the product's usefulness in all applications.

**Product Operating Temperature** -60 to +400°F

The data presented in this document represent typical values for the production material.

The data should not be used to write, or in place of, material specifications.

Please verify that any printed hard copy of this datasheet is current by referencing:

Last Revised July 9th, 2010.

For Pricing and Information please contact distributor: KIEPURA AVIATION CORP.

61 Church St. Littleton, NH 03561

Tel: 603-444-3459 / Fax: 603-444-0790 Toll Free: 1-888-522-8273 (USA/Canada)

Email: jane@kiepuraaviation.com www.kiepuraaviation.com