



western filament, inc.

DATA SHEET FOR 70HOF25G Natural w/tracer

Item number HOF70GTR

SCOPE

This data sheet establishes the requirements of 70HOF25G Natural w/tracer. The item number for this exact product is HOF70GTR.

MATERIAL

The yarn furnished under this data sheet shall be a Nomex® aramid fiber. The yarn shall also be electrical grade, continuous filament, having high insulation resistance, and high dielectric strength. The material shall be coated with a synthetic elastomer. The material shall be natural (off-white) in Color with a dark green tracer.

CONSTRUCTION

The yarn shall be a flat braid configuration.

Width ----- .099" min \ .121" max
Thickness ----- .011" min \ .017" max
Breaking Strength ----- 50 lb. min.
Elongation ----- 40% max.

EFFECTS OF HEAT

The yarn furnished under this data sheet does not melt & does not propagate flame. At about 800°F it carbonizes & forms a tough char.

EFFECTS OF ACIDS AND ALKALIS

The yarn used in this braid is unaffected by most acids, except some strength loss after long exposure to hydrochloric, nitric and sulfuric. It has generally good resistance to alkalis and excellent resistance to mildew and aging. It also has good abrasion resistance.

For Pricing and Information

please contact distributor:

KIEPURA AVIATION CORP.

61 Church St.

Littleton, NH 03561

Tel: 603-444-3459 / Fax: 603-444-0790

Toll Free: 1-888-522-8273 (USA/Canada)

Email: jane@kiepuraaviation.com

www.kiepuraaviation.com