

Elastomeric Material Solutions Division 1100 Governor Lea Road, Bear, DE 19701 (302) 834-2100 (302) 834-4021 (Fax) www.rogerscorp.com/arlon

PRODUCT INFORMATION SHEET

Reference MOX-Tape[®] : ARLON[®] Product Number: 604 - 1 T2040-R004

| PRODUCT DESCRIPTION | | | |
|--|-----------------------------------|---------------------------|--------------------------------------|
| 1.00" wide, 0.040" thick, red, triangular cross- Product is supplied in various yard-long roll I Meets Commercial Item Description A-A-591 packaging. | engths. | 5. | ion MIL-I-46852C) except for |
| Design / Construction | | | |
| Rubber: Cured Self-fusing Silic | Cured Self-fusing Silicone Rubber | | |
| Cross-Section 1.00" Wide Triangular | 1.00" Wide Triangular | | |
| Interleave: 0.001"Mylar | | | |
| Rubber Thickness | | Value | Method |
| Over | all Thickness: | 0.040″ | Arlon SQA-TMS-012 |
| Product Color : Red tape with green guideline | | | |
| TYPICAL PROPERTIES | | | |
| Product Properties | | <u>Value</u> | <u>Method</u> |
| Tensile Strength | lb/in | 1392 | Arlon SQA-TMS-009 |
| Elongation | % | 732 | Arlon SQA-TMS-009 |
| Tear Strength | ррі | 151 | Arlon SQA-TMS-029 |
| Durometer (Silicone Compound) S | hore A Points | 49 | Arlon SQA-TMS-014 |
| Specific Gravity (Silicone Compound) | | 1.2 | Arlon SQA-TMS-024 |
| Dielectric Strength | volts/mil | 498 | Arlon SQA-TMS-020 |
| Bond Strength | lb/in | 3.5 | Arlon SQA-TMS-015 |
| Water Absorption | % | 0.1 | Arlon SQA-TMS-016 |
| SHELF LIFE AND RECOMMENDED OPERATING TEMPERATURE | | | |
| Product Shelf Life12 months from DOM @ 70°F | | | |
| Note: Shelf life is defined as the duration of time for It does not guarantee the product's usefulness in all d | | will meet the physical ch | aracteristics outlined on this page. |
| Product Operating Temperature -60°F to +400°F | | | |

The data presented in this document represents typical values for the production material.

Typical values should not be used for specification limits.

Please verify that any printed hard copy of this datasheet is current by referencing: www.rogerscorp.com/arlon The information contained in this Data Sheet is intended to assist you in designing with Rogers' ARLON Materials. It is not intended to and does not create any warranties, express or implied, including any warranty of merchantability or fitness for a particular purpose or that the results shown in this Data Sheet will be achieved by a user for a particular purpose. The user should determine the suitability of Rogers' ARLON Materials for each application. The Rogers logo, Helping power, protect, connect our world and ARLON are trademarks of Rogers Corporation or one of its subsidiaries. ©2018 Rogers Corporation, All rights reserved. Printed in U.S.A., 0618-PDF, Publication #202-173 For Pricing and Information please contact distributor:

Kiepura Aviation Corp.

61 Church Street Littleton, New Hampshire 03561 USA

Tel: 603-444-3459 Fax:603-444-0790 jane@kiepuraaviation.com www.kiepuraaviation.com



Toll Free: In the US & Canada 888 KAC TAPE 888 522 8273