



900 52152

**Typical Specification Properties
Freudenberg NOK Reinforced Fusion Tape**

**$\frac{3}{4}$ " x 60mil x 36ft
Part Number 90052152**

Thermal Stability Class H ASTM D 2148	180 ⁰ C (355 ⁰ F)
Temperature Rating ASTM D 1418	-65 ⁰ F to +500 ⁰ F
Volume Resistivity, Ohm-cm ASTM D 991	10 ¹³ min (@250 ⁰ F)
Self-Adhesion, inches of unwind ASTM D 2148	2 max
Hardness, Shore A ASTM D 2240	45+/- 5
Moisture Absorption (% Max) (96 hours in H2O @ 70 ⁰ F) ASTM D 471	15
Elongation (% Max) ASTM D412	15
Break Strength (lbs/inch Min) ASTM D 412	100
Dielectric Strength (Volts/MIL min) ASTM D 149	350

**For Pricing and Information
please contact distributor:
KIEPURA AVIATION CORP.**

61 Church St.
Littleton, NH 03561
Tel: 603-444-3459 / Fax: 603-444-0790
Toll Free: 1-888-522-8273 (USA/Canada)
Email: jane@kiepuraaviation.com
www.kiepuraaviation.com