



## **E&H LAMINATING & SLITTING COMPANY**

### **E&H #770-3FRD**

#### **PRESSURE SENSITIVE INSULATION COVER SPLICING TAPE**

**INTENDED USE:** This tape is primarily used in the fabrication of insulation blanket covers and for the installation of insulation blankets. It may be used for sealing sewn seams and for closing fabrication slits or holes around brackets, conduits or other objects that may exist after installation.

**CONSTRUCTION:** Dull Gray Metalized Polyvinyl Fluoride Film  
10x10 visual scrim count with Fire Retardant Acrylic Pressure Sensitive Adhesive

#### **180° PEEL STRENGTH PTSC-1 (ASTM D 3330):**

15 Min.	54.4 oz/inch average
3 Day	129.6 oz/inch average
30 Day	152.3 oz/inch average

#### **TENSILE STRENGTH PSTC-31**

<b><u>ENGLISH</u></b>	<b><u>METRIC:</u></b>
23.6 lbs. / 1" width average	105.02N / 25mm average

**WEIGHT:** 4.5 +/- .3oz/square yard

#### **FLAMMABILITY 12 SECOND VERTICAL BURN:**

Burn Length	3.4 inches maximum
Flame Time	0 Seconds
Drip Flame Time	No Drips

**SHELF LIFE:** Minimum of 12 months in cool, dry storage

#### **PASSES SPECIFICATIONS:**

DMS-1984 Rev. P Type 6 Class 2  
FAA Radiant heat Panel FAR 25.856 (A)  
FAR PART 25.853 (A,B)  
DMS-1511 12 second vertical burn  
BSS-7230 12 second vertical burn

**E&H CO:** As manufacturer warrants that the products described and presented herein are of merchantable quality, but does not warrant their fitness for any particular use or make any other warranty, expressed or implied. Liability of **E&H** under this warranty is limited to replacement of the products found to be defective, or, at its option, a refund of the purchase price.

#### **For Pricing and Information**

**please contact distributor:**

**KIEPURA AVIATION CORP.**

61 Church St.

Littleton, NH 03561

Tel: 603-444-3459 / Fax: 603-444-0790

Toll Free: 1-888-522-8273 (USA/Canada)

Email: [jane@kiepuraaviation.com](mailto:jane@kiepuraaviation.com)

[www.kiepuraaviation.com](http://www.kiepuraaviation.com)