

PRODUCT INFORMATION SHEET

Arlon Product Number T2030-R004-12
MOX 603

PRODUCT DESCRIPTION

1.0 inch wide x 0.030" thick x 12.0 yards long, red, triangular cross-section, silicone, self-fusing tape.

Design / Construction

Interleave: 0.001" PET
Product: Cured Silicone Self Fusing Rubber
Cross-Section: Triangular



<u>Rubber Thickness</u>	<u>Value</u>	<u>Method</u>
Overall Thickness:	0.030"	Arlon SQA-TMS-012

Product Color : Red, Black

PROPERTIES

<u>Silicone Compound Properties</u>		<u>Value</u>	<u>Method</u>
Tensile Strength	psi	1217	Arlon SQA-TMS-009
Elongation	%	706	Arlon SQA-TMS-009
Tear Strength	ppi	135	Arlon SQA-TMS-029
Durometer	Shore A Points	48	Arlon SQA-TMS-014
Specific Gravity	---	1.18	Arlon SQA-TMS-024

<u>Product Properties</u>		<u>Value</u>	<u>Method</u>
Dielectric Strength	volts/mil	597	Arlon SQA-TMS-020
Bond Strength	lb/in	3.0	Arlon SQA-TMS-015
Water absorption	%	0.1	Arlon SQA-TMS-016

SHELF LIFE & CONTINUOUS OPERATING TEMPERATURE

Product Shelf Life 12 months from DOM @ 70°F

Note: Shelf life is defined as the duration of time for which the product will meet the physical characteristics outlined on this page. It does not guarantee the product's usefulness in all applications.

Product Operating Temperature -60 to +400°F

The data presented in this document represent typical values for the production material. The data should not be used to write, or in place of, material specifications.

Last Revised April 16th, 2012.

For Pricing and Information
please contact distributor:
KIEPURA AVIATION CORP.
 61 Church St.
 Littleton, NH 03561
 Tel: 603-444-3459 / Fax: 603-444-0790
 Toll Free: 1-888-522-8273 (USA/Canada)
 Email: jane@kiepuraaviation.com
www.kiepuraaviation.com