



western filament, inc.

DATA SHEET FOR 25NOF9W

Per A-A-52080, Finish B, Size 5

SCOPE

This data sheet establishes the requirements of 25NOF9W.

MATERIAL

The yarn furnished under this data sheet shall be nylon. The finished tape is coated with a microcrystalline fungicide wax. Available in colors Natural or Black.

CONSTRUCTION

The yarn shall be braided in a flat braid configuration.

Width ----- .045" min. / .055" max.

Thickness ----- .006" min. / .014" max.

Tensile Strength ----- 15 lb. Min.

EFFECTS OF HEAT

Material sticks at 445°F and melts at 480°F - 500°F.

EFFECTS OF ACIDS AND ALKALIS

Unaffected by most mineral acids. Soluble in formic acid. Substantially inert in alkalis.

SHELF LIFE

The shelf life has a minimum of five years when stored at temperatures of 100° F or less.

For Pricing and Information

please contact distributor:

KIEPURA AVIATION CORP.

61 Church St.

Littleton, NH 03561

Tel: 603-444-3459 / Fax: 603-444-0790

Toll Free: 1-888-522-8273 (USA/Canada)

Email: jane@kiepuraaviation.com

www.kiepuraaviation.com