

PRODUCT INFORMATION SHEET

Reference MOX-Tape® : 630 - 1
Arlon Product Number T1030-B004

PRODUCT DESCRIPTION

1.0 inch wide, 0.030" thick, black, rectangular cross-section, silicone self-fusing tape.
Product is supplied in various yard long roll lengths.

Design / Construction

Product: Cured self-fusing silicone rubber
Cross-Section 1.0" wide Rectangular
Interleave: 0.001" polyester film



<u>Rubber Thickness</u>	<u>Value</u>	<u>Method</u>
Width	1.0"	Arlon SQA-TMS-012
Overall Thickness:	0.030"	Arlon SQA-TMS-012

Product Color : Black

TYPICAL PROPERTIES

<u>Product Properties</u>	<u>Value</u>	<u>Method</u>
Tensile Strength psi	1459	Arlon SQA-TMS-009
Elongation %	731	Arlon SQA-TMS-009
Durometer Shore A Points	52	Arlon SQA-TMS-014
Specific Gravity ---	1.2	Arlon SQA-TMS-024
Dielectric Strength volts/mil	619	Arlon SQA-TMS-020
Bond Strength lb/in	2.8	Arlon SQA-TMS-015
Water Absorption %	0	Arlon SQA-TMS-016

SHELF LIFE AND RECOMENDED OPERATING TEMPERATURE

Product Shelf Life 12 months from DOM @ 70°F

*Note: Shelf life is defined as the duration of time for which the product will meet the physical characteristics outlined on this page.
It does not guarantee the product's usefulness in all applications.*

Product Operating Temperature -60 to +400°F

The data presented in this document represent typical values for the production material.

The data should not be used to write, or in place of, material specifications.

Please verify that any printed hard copy of this datasheet is current by referencing:

<http://www.rogerscorporation.com>

Last Revised May 14, 2016.

NOTE: The above properties are published as a guide only, and should not be used for specification without testing in your own laboratory.

For Pricing and Information please contact distributor:

Kiepura Aviation Corp.

61 Church Street

Littleton, New Hampshire 03561 USA

Tel: 603-444-3459
Fax: 603-444-0790
jane@kiepuraaviation.com
www.kiepuraaviation.com



Accredited according to
ASA-100 and FAA AC 00-56B

Toll Free: In the US & Canada
888 KAC TAPE
888 522 8273