

PRODUCT INFORMATION SHEET

Reference MOX-Tape® : SA01015
Arlon Product Number : T3015-R004

PRODUCT DESCRIPTION

Design / Construction

Side 1: Cured fusible silicone rubber
Substrate: 25% sinusoidal fiberglass
Side 2: Cured fusible silicone rubber
Interleave 0.001" polyester film



Dimensions

	Value	Method
Width:	1.00"	Arlon SQA-TMS-012
Overall Thickness:	0.015"	Arlon SQA-TMS-012

Product Color : Red

PROPERTIES

Silicone Compound Properties

	Value	Method
Tensile Strength psi	1198	ASTM D 412
Elongation %	580	ASTM D 412
Tear Strength (Die B) lb/in	124	ASTM D 624
Durometer Shore A Points	50	ASTM D 2240
Specific Gravity ---	1.2	Arlon SQA-TMS-024

Substrate Properties

	Value	Method
Thickness	0.008"	Arlon SQA-TMS-012
Color	Naturally White	N/A

Tape Properties

	Value	Method
Dielectric Breakdown Strength volts/mil	563	ASTM D 149
Elongation %	28	Arlon SQA-TMS-048
Tensile Strength Lb/in	61	Arlon SQA-TMS-048
Adhesion strength Lb/in	4.3	Arlon SQA-TMS-047

SHELF LIFE & OPERATING TEMPERATURE

Product Shelf Life 12 months from date of manufacture @ 70°F
Note: Shelf life is defined as the duration of time for which the product will meet the physical characteristics outlined on this page.
It does not guarantee the product's usefulness in all applications

Recommended Cure Cycle N/A

Recommended Post Cure Cycle N/A

Product Operating Temperature -70°F to 450°F

UL INFORMATION

File : N/A

The data presented in this document represent typical values for the production material.

The data should not be used to write, or in place of, material specifications.

Please verify that any printed hard copy of this datasheet is current by referencing:

<http://www.rogerscorporation.com/Library/datasheets.htm>

Last Revised May 14, 2016.

NOTE: The above properties are published as a guide only, and should not be used for specification without testing in your own laboratory.

For Pricing and Information please contact distributor:

Kiepura Aviation Corp.

61 Church Street

Littleton, New Hampshire 03561 USA

Tel: 603-444-3459
Fax: 603-444-0790
jane@kiepuraaviation.com
www.kiepuraaviation.com



Accredited according to
ASA-100 and FAA AC 00-56B

Toll Free: In the US & Canada
888 KAC TAPE
888 522 8273