# DW469

Thermal Spray Tape



DeWAL® DW469 is a pressure sensitive tape made of closely woven glass fabric and high temperature silicone adhesive. The glass fabric has excellent abrasion and heat resistance.

### Applications:

- Masking tape in grit blasting, plasma, and flame spraying
- Splicing and position in coils and support rings
- Reinforcing slot insulation and armature coil insulation
- Transformers, solenoids and appliances
- Splice Outer Wraps

(800) 935-2940 • solutions@rogerscorp.com

## Industry(s):

- Aerospace
- Electrical
- Military/Defense
- Oil/Gas
- Plasma & Thermal Spray Masking
- Wire and Cable

## Features and Benefits

- · High temperature resistance
- Abrasion resistance

| Basic Physical Properties   | Typical Value  | Units  | Test Method   |
|---|--|--|---|
| Dielectric Strength   | 237.8 / 604  | kV/cm / V/mil  | ASTM D149   |
| Adhesion to Steel   | 491 / 44   | g/cm / oz/in   | ASTM-D 1000   |
| Color   | White  | N/A  | N/A   |
| Construction  | Typical Value  | Units  | Test Method   |
| Substrate   | Glass Cloth  | N/A  | N/A   |
| Adhesive System   | Silicone   | N/A  | N/A   |
| Adhesive Thickness  | 0.056 / 0.0022   | mm / in  | N/A   |
| Overall Thickness   | 0.1778 / 0.007   | mm / in  | ASTM-D374   |
| Min Width   | 6.35 / 0.25  | mm / in  | N/A   |
| Max Width   | 914 / 36   | mm / in  | N/A   |
|   |  |  |   |
| Heat and Flame  | Typical Value  | Units  | Test Method   |
| Heat and Flame<br>Max Operating Temp.   | Typical Value<br>260 / 500   | Units<br>°C / °F   | Test Method   |
|   |  |  |   |
| Max Operating Temp.   | 260 / 500<br>510A File No. E179854 Flame   | °C / °F  | N/A   |
| Max Operating Temp.<br>UL Rating  | 260 / 500<br>510A File No. E179854 Flame<br>Retardant  | °C / °F<br>N/A   | N/A<br>N/A  |
| Max Operating Temp.<br>UL Rating<br>Processing & Packaging  | 260 / 500<br>510A File No. E179854 Flame<br>Retardant<br>Typical Value                                       | °C / °F<br>N/A<br>Units  | N/A<br>N/A<br>Test Method                             |
| Max Operating Temp.<br>UL Rating<br>Processing & Packaging<br>Shelf Life  | 260 / 500<br>510A File No. E179854 Flame<br>Retardant<br>Typical Value<br>1                                  | °C / °F<br>N/A<br>Units<br>Year from DOM                             | N/A<br>N/A<br>Test Method<br>N/A                      |
| Max Operating Temp.<br>UL Rating<br>Processing & Packaging<br>Shelf Life<br>Shelf Life Storage Temp.                                      | 260 / 500<br>510A File No. E179854 Flame<br>Retardant<br>Typical Value<br>1<br>21 / 70                       | °C / °F<br>N/A<br>Units<br>Year from DOM<br>°C / °F                  | N/A<br>N/A<br>Test Method<br>N/A<br>N/A               |
| Max Operating Temp.<br>UL Rating<br>Processing & Packaging<br>Shelf Life<br>Shelf Life Storage Temp.<br>Roll Length                       | 260 / 500<br>510A File No. E179854 Flame<br>Retardant<br>Typical Value<br>1<br>21 / 70<br>33 / 36            | °C / °F<br>N/A<br>Units<br>Year from DOM<br>°C / °F<br>m / yd        | N/A<br>N/A<br>Test Method<br>N/A<br>N/A<br>N/A        |
| Max Operating Temp.<br>UL Rating<br>Processing & Packaging<br>Shelf Life<br>Shelf Life Storage Temp.<br>Roll Length<br>Standard Core Type | 260 / 500<br>510A File No. E179854 Flame<br>Retardant<br>Typical Value<br>1<br>21 / 70<br>33 / 36<br>Plastic | °C / °F<br>N/A<br>Units<br>Year from DOM<br>°C / °F<br>m / yd<br>N/A | N/A   N/A   Test Method   N/A   N/A   N/A   N/A   N/A |

#### Specifications

Specification(s)

GE: C10 - 12, PMC 4273, RR: OMAT 2/203, UL 510A File No. E179854

• Typical values shown are from testing at date of manufacture and should not be used for specification limits.

· Additional technical information and product specifications are available upon request.

• Shelf life is 1 year from the date of manufacture with storage conditions of 21°C (70°F) and 50% RH.

• All metric conversions are approximate.

Note: Shelf life is defined as the duration of time for which the product will meet the physical characteristics outlined on this page. It does not guarantee the product's usefulness in all applications.



The information contained in this Data Sheet is intended to assist you in designing with Rogers' Elastomeric Material Solutions. It is not intended to and does not create any warranties, express or implied, including any warranty of merchantability or fitness for a particular purpose or that the results shown in this Data Sheet will be achieved by a user for a particular purpose. The user should determine the suitability of Rogers DeWAL products for each application. The Rogers logo, DeWAL logo and DeWAL are trademarks of Rogers Corporation or one of its subsidiaries.

© 2025 Rogers Corporation. All rights reserved. www.rogerscorp.com. Modified: 04/09/2025